## **Technical Information Sheet**



# QuickSeam™ R.M.A. Strip

#### 1. Description

The Firestone QuickSeam™ R.M.A. Strip is a 254 mm (10") wide strip of Firestone RubberGard™ EPDM MAX reinforced membrane with two Firestone QuickSeam™ Tape strips factory laminated to it along its length. The QuickSeam R.M.A strip is used for non-penetrating RubberGard™ EPDM membrane attachment, as specified in the Firestone guidelines.



### 2. Preparation

The substrate needs to be clean, smooth, dry and free of sharp edges, loose or foreign materials, oil, grease and other materials that may damage the material. Restore to room temperature prior to use, if exposed to temperatures below 15°C for prolonged periods.

#### 3. Application

Unroll the QuickSeam R.M.A. Strip with the release paper up in accordance with the layout plan specified. Once the strip lays flat, fasten it to the substrate with Firestone Batten Strips or approved plates and fasteners. Apply QuickPrime Plus to the back of the RubberGard EPDM membrane. When the primer is dry, remove the release papers from the QuickSeam R.M.A. Strip and roll the membrane onto the strip. Roll the strips using the QuickRoller or a silicon rubber roller to ensure proper adhesion. Refer to the Firestone guidelines for specific installation instructions.

#### 4. Coverage

In accordance with length of mechanical attachment.

#### 5. Characteristics

Technical		
	RubberGard MAX	QuickSeam Tape (2 x)
<ul> <li>Base</li> </ul>	EPDM	Rubber polymers
<ul> <li>Color</li> </ul>	Black	Black
<ul> <li>Solvents</li> </ul>	None	None
<ul> <li>Solids</li> </ul>	100 %	100 %
<ul> <li>Thickness</li> </ul>	1.2 mm ± 20 %	0.6 mm ± 0.1 mm
<ul><li>Width</li></ul>	254 mm	76 mm

### 6. Packaging / Storage / Shelf Life

Packaging	30.5 m (100') rolls, 1 roll per carton
Part number	W56RAC1610 - 254 mm (10")

Note: Firestone QuickScrubber $^{\text{\tiny{M}}}$  and/or QuickScrubber $^{\text{\tiny{M}}}$  Plus pads and handles are included in each carton. Quantities vary depending on the QuickSeam product.

**Storage:** Store in original unopened containers at temperatures between 15°C and 25°C, in a well-ventilated place. Keep the material dry and out of direct sunlight until ready for application.

**Shelf Life:** 24 months can be expected if stored in above-mentioned conditions. Verify production date on each roll. Shelf life will be reduced if exposed to higher temperatures. Shelf life information is only a recommendation and not a fact of life. The real expiration date highly depends on the history of storage and handling of the accessories.



# **Technical Information Sheet**



_	_			•	
7	Dν	eca	2111	10	nc
	г		3 U I		

Refer to Safety Data Sheet.

This document replaces any other document published previous. This sheet is meant to highlight Firestone product information based on latest knowledge and experience and is subject to change without notice (check the Firestone website for latest document version). Above mentioned values are based on tested samples and may vary within applicable tolerances. Firestone takes responsibility for furnishing quality materials which meet published Firestone product specifications. No Firestone representative is authorized to vary this disclaimer.