Technical data sheet BauderSYN DB-PE 100 Polyethylene AVCL



06/06/2024

| Product description | Polyethylene air & vapour control layer to be loose laid under BauderTHERMOFOL mechanically fastened installations | and the same of th |
|---------------------|--------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Surface | Plain foil | |
| Colour | Blue | |
| Article number | 6900 0025 | |

| Characteristic | Test method | Unit | Value |
|---------------------------------------------|--------------|--------|--------------------|
| Visible defects | EN 1850-2 | - | no visible defects |
| Length | EN 1848-2 | m | 25 |
| Width | EN 1848-2 | m | 4 |
| Mass per unit area | EN 1849-2 | g/m² | 150(+/-7%) |
| Effective thickness | EN 1849-2 | mm | 0,16 |
| Water tightness | EN 1928 - B | - | passed |
| Reaction to fire | EN 13501-1 | - | class E |
| Heating value | EN 13431 | MJ/m² | <11,6 |
| Joint shear resistance | EN 12317-2 | N/50mm | NPD |
| Tensile strength Id | EN 12311-2 B | N/50mm | ≥170 |
| Tensile strength td | EN 12311-2 B | N/50mm | ≥140 |
| Elongation Id | EN 12311-2 B | % | ≥490 |
| Elongation td | EN 12311-2 B | % | ≥550 |
| Resistance to impact hard surface | EN 12691 | mm | ≥300 |
| Tear resistance (length) | EN 12310-2 | N | > 120 |
| Tear resistance (transversal) | EN 12310-2 | N | > 120 |
| Diffusion equivalent air layer thickness sd | EN 1931 | m | ≥ 100 |
| Durability after artificial ageing | EN 1296 | - | passed |
| Package size | - | - | 100 m² |
| External fire performance | CEN/TS 1187 | - | not applicable |

Installation guidance

Polyethylene AVCL joints should overlap a minimum of 100 mm and be taped in the field sheet with



Notified body: SKZ TeConA GmbH , NB 1213

EN 13984

Technical data sheet BauderSYN DB-PE 100 Polyethylene AVCL



BauderSYN VK-T 38. Use BauderSYN BU-T 15 for upstands. Not uv stable, product should be covered

immediately.

Product storage guidance Store the materials outdoors, laid horizontal/flat and off the ground with suitable robust UV resistant,

flame-retardant tarpaulin. Ensure the product(s) are clear of buildings and any other storage areas. Where

there are storage containers on site, these may be suitable for storing products.

Pallet size = 54 rolls/ 5400 m² per pallet

Packaging material The product will be delivered on wooden pallets with polyethylene overwrap to protect the product. Each roll

has a recycled cardboard core. Recycled nylon straps contain the rolls on a pallet.

Handling/PPE All persons using the product should be fully aware of the manual handling methods as roofing materials are

heavy and can cause serious injury. When using/handling the product, installers should be provided with, and

wear, suitable personal protective equipment.

Disposal guidance Waste of the product is not a hazardous substance. Observe local regulations. European Waste Catalogue

EWC number 170203 "Plastic Mirror Non hazardous".

visiting www.bauder.co.uk

Safety Data Sheet Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures

in the EU & UK. This product is classed as an article; therefore, this product does not have a requirement for a

Safety Data Sheet.



Notified body: SKZ TeConA GmbH , NB 1213